

Technical Data Sheet

Cri-plastMP™ F-TPX Compounds 200C, Low/Medium Voltage Wire & Cable Applications (E-beam Cross-linkable)

Cri-plastMP™ F-TPXs are a family of melt processable, cross-linkable, Fluoro - Thermoplastic Elastomers (F-TPEs) developed to meet a wide range of applications including Automotive, Wire & Cable, Chemical Industry applications. Specific grades can be processed by extrusion and injection molding.

Special Features

- E-Beam Cross-linkable
- Chemical Resistance
- Flexibility
- Heat Resistance
- Melt Processable
- Low Permeation

Typical applications

- Wire & Cable
- Fuel and Chemical transfer
- Tubing/sheet/film

Typical Property Data

Cri-plastMP™ F-TPXs for Wire and Cable Applications			
		Cri-plastMP™ F-TPX*	
		As compounded	After E-beam Crosslinking
MFI	g/10 min @ 200C (10kg weight)	~1-2	na
Specific Gravity		1.85	1.85
Hardness	Shore A pts	80-90	tbd
Tensile	psi	700	~2000
Elongation	%	>500	~200
Modulus	100% psi	600	1,500
Tear Strength	ppi	tbd	tbd
Volume Resistivity	ASTM D257 Plaque testing Ω·mm		~10 ¹⁴
	ISO 19642 Wire testing Ω·mm		tbd

* Data will vary based on specific compound formulation.

Extrusion Processing Guide

- Extrusion Equipment
 - Cri-plastMP F-TPE resins are processed using single screw extruders with an L/D ratio of 24/1 or higher.
 - The extruder is most commonly outfitted with a general purpose, chrome plated 4140 stainless steel metering screw with a 3 to 1 compression ratio having equal length feed, transition (compression) and metering zones.
 - A barrier screw profile is recommended for better melt homogeneity and high-speed extrusion.

- Process temperature profiles:

<u>Barrel Section</u>	<u>Temperature (C)</u>
Feed*	190 – 210
Transition	210 - 230
Metering	220 – 240
Tooling	240 – 250

*Softer durometers may require lower feed temps to avoid tackiness / bridging

230-250 C typical melt temperature

- Screen Pack/mesh
 - 60 mesh with appropriate backer support screen.
- Water bath
 - A water bath is desirable with typical water temperature of 23 to 40C.
- Drying guidelines
 - It is not generally necessary to dry this product. If drying is required, care needs to be taken not to cause the pellets to agglomerate.
 - 2 hours at 90 C will remove any surface moisture.
- E-beam exposure data and dosage
 - Typical data characterization was done at 10 MRads on a ~.020” thick tape.
 - Test exposure for 1 Mrad on the VDG system, we used the following conditions:
 - Voltage 2.6 MeV
 - Beam .5 mA
 - Scan Area 15”
 - Window distance to target: 5”
 - Conveyor speed 50 Inches p/minute